





Rigid Thermal Insulation



Learn more about rigid thermal insulation products made of OPCORE® at www.opcodirect.com

RECYCLABLE THERMAL INSULATION



OPCORE is Rigid Thermal Insulation, done right.

3rd Party Recognized 'Meet or Exceed Code' Rigid Thermal Insulation Performance

OPCORE[®]

OPCORE Performs Better when it's Colder and, it's R-value performance is stable over time.

OPCORE is made of small pockets of air surrounded by a recyclable polymer matrix. This means the R-value of the material is stable over time.

Chart illustrates R-value per inch of thickness as a function of density and temperature, measured in accordance with ASTM Test Method C518. R-values can be higher than the minimum R-value for a given ASTM C-578 'Type' because ASTM C-578 Types specify a minimum R-value.





RECYCLABLE THERMAL INSULATION





Expecting Rain?

OPCORE plays well with Moisture Vapor <u>and</u> Bulk Water

Water and moisture are ever-present, so managing their presence is paramount to a building's longevity. OPCORE can keep bulk water on the outside. Greater water vapor permeability can help reduce the risk of vapor condensation inside the wall.

A Decades-Long Stable R-value is just the beginning of OPCORE's Sustainability Story

- OPCORE is recyclable as a #6 polymer compound
- Reduces use of resources in the manufacture, transportation and use of more dense insulation products
- Comprised of up to 98% air
- Contains no ozone-depleting CFC's, HCFC's, HFC's, nor formaldehyde
- Combination of recyclable polymer matrix and air enables the material to exhibit a long-term stable R-value





Dimensional Accuracy & Consistency means you get a Superior Thermal Envelope

Quality matters. OPCORE meets stringent performance and quality certifications. OPCORE can be sized to your specifications using proprietary processes. Thickness, length and width dimensions can be specified accurate to 1/16 of an inch on dimensions between 4" and 96". This means fewer problems during installation and a more consistent thermal envelope.

Metric	Thickness	Length	Width
Tolerance (in/in)	1/16″	1/16″	1/16"
Range	1/2" < t < 48"	1/2"< <216"	1/2" < w < 36"

OPCORE [®] Physical Properties Nominal Rigid Foam Density in lbs/cubic foot, ASTM C303, lbs/ft ³										
Property	Method	Units	0.90	1.15	1.35	1.80	2.40	3.00		
Compressive Resistance	ASTM D1621	At yield of 10% deformation in psi (kPa)	10 (69)	13 (90)	15 (104)	25 (173)	40 (276)	60 (414)		
Contribution to Sustainable Practices			Recyclable as #6 Plastic. Can contain recycled content per specification Retains R-value over time. Does not contain chlorofluorocarbons. UL GreenGuard Certified for Indoor Air Quality. Material expansion agent has zero ozone depletion potential.							
Compliance with ASTM C578 ⁽¹⁾	ASTM C578	Туре	I	VIII	II	IX	XIV	XV		
Thermal Resistance (R-value*) , 75F ⁽²⁾	ASTM C518	per inch of thickness in °F•ft²•h/ BTU (K•m²/W) 75 ±2°F (23.9 ±1°C)	3.6	3.8	4.0	4.2	4.2	4.3		
Thermal Resistance (R-value*), 40F ⁽²⁾	ASTM C518	per inch of thickness in °F•ft²•h/ BTU (K•m²/W) 40 ±2°F (4.4 ±1°C)	3.9	4.2	4.3	4.5	4.6	4.6		
Thermal Resistance (R-value*), 25F ⁽²⁾	ASTM C518	per inch of thickness in °F•ft²•h/ BTU (K•m²/W) 25 ±2°F (-3.9 ±1°C)	4.1	4.3	4.4	4.6	4.7	4.7		
Flexural Strength	ASTM C203	psi (kPa)	25 (173)	30 (208)	35 (242)	50 (345)	60 (414)	75 (517)		
Water Vapor Permeance ⁽³⁾	ASTM E96	For 1″ (25.4 mm), perm (ng/ PA∙s∙m²), max	5.0	3.5	3.5	2.5	2.5	2.5		
Water Absorption by Total Immersion	ASTM C272	Volume % absorbed, max	4.0	3.0	3.0	2.0	2.0	2.0		
Dimensional Stability	ASTM D2126	max % linear change	< 1.5							
Oxygen Index	ASTM D2863	volume %	> 24							
Surface Burning Characteristics	ASTM E-84 or UL 723	Flame Spread / Smoke Developed	Flame Spread <25, Smoke Developed <450							
Biological Behavior			Will not support growth of mold or mildew. No harmful effects on health known.							
Chemical Resistance			Insensitive to water, the majority of acids and alkalis; sensitive to organic solvents.							
Application Limiting Temperature		°F/°C	165 (73.9) nominal / 180 (82.2) max							

(1) OPCORE meets and/or exceeds ASTM C578-11b "Standard Specification For Preformed, Cellular Polystyrene Insulation"; published by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959.

(2) R-value means resistance to heat flow. The higher the R-value, the greater the insulating power. Ask your seller for the fact sheet on OPCORE R-values. The R-value properties are based on 1 in thickness.

(3) Values quoted are maximum values for 1 inch (25mm) thick samples and are based upon most recent raw material product quality audit data. Actual water vapor permeance data decreases as thickness increases. Where water vapor permeance is a design concern, use of the product is subject to professional engineering review at the specifiers option.

* The higher the R-value, the greater the insulating power. The physical property data shown above are presented as typical average values as determined by industry accepted and standard test methods, except where noted, and are subject to normal manufacturing variation. ASTM specifications shown are typical for rigid, cellular polystyrene thermal insulation and are published by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959.



Opco, Inc. 205 W Harrison Avenue Latrobe, PA 15650 Tel: 724.537.9300 / 800.229.6726 Fax: 724.537.9349 www.opcodirect.com



The information contained herein is subject to change and is provided for informational purposes only is provided without warranty, either express or implied. Opco reserves the right to amend the information in this publication without notice. Opco, Inc. nor Intuitive Marketing and Engineering, LLC assume no liability for any errors or omissions in the content of this publication.

Copyright 2019 Opco, Inc. all rights reserved. OPCORE is a registered trademark of Opco, Inc. The OPCO logo and OPCORE are trademarks of Opco, Inc. The UL logo is a registered trademark of UL LLC. The GREENGUARD Certification mark is a trademark of UL LLC. The SIPA mark is a trademark of the Structural Insulated Panel Association. The ICC-ES Certification mark is a trademark of ICC Evaluation Service, LLC. The OAI Certification mark is a registered trademark of QAI Laboratories. The NTA certification mark is a registered trademark of NTA, Inc.. Any use of this publication, including reproduction, modification, distribution or republication without prior written consent is strictly prohibited.

Pub. No. 1903-OPTI-019. Printed in U.S.A.